

ADDENDUM #3 - JULY 9, 2010

RE: **COOS BAY SCHOOLS
2010 PAINTING PROJECT
PROJECT #10.34**

FROM: HGE INC., Architects, Engineers, Surveyors & Planners
375 Park Avenue
Coos Bay, Oregon 97420
541-269-1166



TO: Prospective Bidders

This Addendum forms a part of the Contract Documents and modifies the original Documents dated June 2010, as noted below. Acknowledge receipt of this Addendum in the space provided on the Bid Form. Failure to do so may subject Bidder to disqualification.

This Addendum consists of 2 pages.

CHANGES TO ADDENDUM #1

1. Delete Item #3 in its entirety.

CHANGES TO SPECIFICATIONS

1. Section 09800 - Elastomeric Coatings, subparagraph 2.01.A.4: Change "Conflex XL" to "Loxon XP".
2. Section 09800 - Elastomeric Coatings, subparagraph 2.01.A.: Add the following item:
"5. Benjamin Moore, "Moorlastic" Acrylic Elastomeric Fine Texture 060 (South facade only)."
3. Section 09800 - Elastomeric Coatings, subparagraph 2.01.C: Add the following item:
"2. Moorlastic Knife Grade Elastomeric Patch."
4. Section 09800 - Elastomeric Coatings, subparagraph 3.03: Delete in its entirety and replace with the following:
"A. Elastomeric Coating.
1. Brush, spray, or roller apply coating material at a coverage rate of 90 to 100 square feet of surface area per gallon of material for each coat, 40-45 square feet of surface area per gallon total. Mix each pail to assure color uniformity, aggregate disbursement, and minimize air entrapment. Stripe coat all inside and outside corners, and edges with one additional coat."

2. Thickness:
 - a. Total wet film thickness shall be 20 mils per coating. Two coatings required, with an additional coat at all edges and corners (stripe coat).

- B. Fine Texture Elastomeric Coating (South Wall).
 1. Roller apply coating material at a coverage rate of 40-80 square feet of surface area per gallon of material for each coat, 20-40 square feet of surface area per gallon total. Ensure that coating mixture is both uniform in color and consistency, and minimize air entrapment. **Do not thin** or apply if rain or threatening weather is anticipated within the next 24 hours. Ensure that the finish contains no more than five pinholes per square foot, to ensure a waterproof finish. Apply first coat horizontally and second coat vertically. Stripe coat all inside and outside corners, and edges with one additional coat.
 2. Thickness:
 - a. Total wet film thickness shall be 30 mils per coating. Two coatings required, with an additional coat at all edges and corners (stripe coat).

- C. Other Materials.
 1. Install all other materials per manufacturer's specifications.”

END OF ADDENDUM